

Protac™ Canvastex UV

PCT
100μ

Product Description

Protac™ Canvastex UV is a 100μ (4 mil) canvas finish, Monomeric Calendared PVC laminating film coated on one side with a pressure sensitive, solvent acrylic adhesive, which is protected by a one side siliconised polyester release liner. Both the film and the adhesive contain UV stabilisers, which protect against both UV degradation and potential mechanical damage. Protac™ Canvastex UV has been awarded a **Class 0 Fire Rating**, when tested against BS476:Part6:1989+A1:2009 and BS476:Part7:1997 requirements. Available in various sizes.

Applications

The most common applications for Protac™ Canvastex are portrait photography, book and album covers, framed mats, diplomas and certificates. Protac™ Canvastex is also used on posters to simulate the look of an original oil painting.

Product Structure

Film:	Canvas textured Monomeric Calendared PVC
Adhesive:	Solvent Acrylic (pressure sensitive)
Release Liner:	One side siliconised polyester

125μ
(5 mil)

General Properties

Film Thickness	100μ (4 mil)
Adhesive Layer	25μ (1 mil)
Ratio Film to Adhesive	4:1
UV Protection Factor	Film and adhesive contains UV stabilisers, which prevent film degradation and provides UV protection to the underlying image.
Outdoor Durability	3+ years
Heat Resistance Range	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	15 N/25mm

Process Settings

Roller Laminator	Vacuum Press
Temp: Room temp to 49°C (120°F) Speed: 0.3m to 2.5m (1ft to 8ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to careful quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale.

Drytac Europe Ltd (UK) - Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660
Drytac Corp. (USA) - 5601 Eastport Boulevard, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610
Drytac Canada Inc. (Canada) - 137 Buttermill Avenue, Concord, Ontario, L4K 3X5, Canada. Tel: 1-800-353-288